SPECIFIC GRAVITY AND ABSORPTION OF FINE AGGREGATE FOP FOR AASHTO T 84

Scope

This procedure covers the determination of bulk, bulk (SSD), and apparent specific gravities; and the absorption of fine aggregate after a prescribed soaking period in water in accordance with AASHTO T 84-13. For materials that do not readily slump during the cone test, see AASHTO T 84.

Apparatus

- Balance: A balance of sufficient capacity, readable to 0.1 g. Meeting AASHTO M 231, class G2.
- Pycnometer: A flask or other suitable container in which the volume can be reproduced within ±0.1 ml. The volume of the flask shall be at least 50 percent greater than required for the test sample.
- Mold: A metal mold in the form of a frustum of a cone 40 ±3 mm in diameter at the top, 90 ±3 mm in diameter at the bottom, and 75 ±3mm in height.
- Tamper: A metal tamper weighing 340 ±15 g and having a flat circular tamping face 25 ±3 mm in diameter

Sample Preparation

- 1. Obtain sample according to the FOP for AASHTO R 90
- 2. Reduce according to the FOP for AASHTO R 76.
- 3. Sieve sample over the 4.75 mm (No. 4) sieve.
- 4. Split or quarter approximately 1000 g of material from the portion passing the 4.75 mm (No. 4) sieve.
- 5. Dry to constant mass according to the FOP for AASHTO T 255 using a controlled heat source.
- 6. Cool to room temperature.
- 7. Cover sample with water and allow to stand for 15 to 19 hours.
- 8. Carefully decant the water without losing fines.
- 9. Spread the sample on a flat smooth surface exposed to a gently moving current of warm air.
- 10. Stir frequently to promote uniform drying.
- 11. Continue until the test sample approaches a surface-dry condition.
- 12. To determine a surface-dry condition:
 - a. Hold the mold firmly on a smooth non-absorbent surface (large diameter down).

- b. Fill the mold to overflowing with a portion of the partially dried sample.
- c. Lightly tamp the surface 25 times with the tamper (allow the tamper to fall freely from approximately 5 mm above the top of the sample).
- d. Clean excess from around the base of the mold
- e. Lift the mold vertically.
- f. If the material slumps slightly upon removal of the mold, the sample has reached surface-dry condition.
- *Note 1*: If the fine aggregate slumps on the first trial, it is already too dry. Thoroughly mix a few milliliters of water with the aggregate and permit the sample to stand in a covered container for 30 minutes. Then resume the process of drying and testing for the free-flowing condition.
 - g. If the material does not slump, continue drying while constantly stirring.
 - h. Perform Steps 12a through 12e at frequent intervals until the material reaches a surface-dry condition.

Procedure

Record all masses to the nearest 0.1 g.

- 1. Obtain approximately half, 500 ± 10 g, of the surface-dry material. Designate as S.
- 2. Determine and record mass of *S*.
- 3. Obtain approximately the same amount of material as the mass of S, ± 0.2 g, from the remaining surface-dry material, if desired. Designate as S_1 . This portion of the sample may be used in Step 12.
- 4. Partially fill the pycnometer with water.
- 5. Introduce the sample, *S*, into the pycnometer.
- 6. Fill pycnometer with water to approximately 90 percent capacity.
- 7. Roll, invert, and agitate the pycnometer to eliminate all air bubbles.
- *Note 2:* It normally takes 15 to 20 min to eliminate air bubbles by manual methods. Dipping the tip of a paper towel into the pycnometer has been found to be useful in dispersing the foam that sometimes builds up when eliminating the air bubbles.
- 8. Adjust the temperature of the pycnometer, sample, and water to $23 \pm 1.7^{\circ}$ C (73.4 ±3°F). Immerse in circulating water if necessary.
- 9. Fill pycnometer to its calibrated capacity and dispel any foam.
- 10. Dry the outside of the pycnometer.
- 11. Determine and record the total mass of the pycnometer, sample, and water to the nearest 0.1 g. Designate as *C*.
- 12. Remove the sample from pycnometer and dry to constant mass according to the FOP for AASHTO T 255; or dry the portion of the sample from Step 3 (*S*₁), to constant mass according to the FOP for AASHTO T 255.
- 13. Cool the sample (S or S_1) to room temperature.

14. Determine and record the mass of the dry sample. Designate as A.

Calculations

Bulk Specific Gravity (G_{sb})

$$G_{sb} = \frac{A}{B+S-C}$$

Bulk Specific Gravity (Saturated Surface-dry (SSD)) (GsbSSD)

$$G_{sb}SSD = \frac{S}{B+S-C}$$

Apparent Specific Gravity (Gsa)

$$G_{sa} = \frac{A}{B+A-C}$$

Percent absorption

% absorption =
$$\frac{S \text{ or } S_1 - A}{A} \times 100$$

where:

- A = mass of oven-dry sample in air, g
 B = mass of pycnometer filled with water (see Annex), g
 C = mass of pycnometer, sample, and water, g
 S = mass of saturated surface-dry sample, g
- S_1 = mass of second saturated surface-dry sample, g

Example

Bulk Specific Gravity (Gsb)

$$G_{sb} = \frac{499.0 \ g}{666.1 \ g + 502.3 \ g - 979.1 \ g} = 2.636$$

Bulk Specific Gravity (Saturated Surface-dry (SSD) Basis) (GsbSSD)

$$G_{sb}SSD = \frac{502.3 \ g}{666.1g + 502.3 \ g - 979.1 \ g} = 2.653$$

Apparent Specific Gravity (Gsa)

$$G_{sa} = \frac{499.0 \ g}{666.1 \ g + 499.0 \ g - 979.1 \ g} = 2.683$$

Percent absorption

% absorption =
$$\frac{502.3 \ g - 499.0 \ g}{499.0 \ g} \times 100 = 0.661\%$$
 Report = 0.7%

where:

$$A = 499.0 g$$

$$B = 666.1 g$$

$$C = 979.1 g$$

$$S = 502.3 g$$

$$S_1 = 502.1 g$$

Report

- Report on standard agency forms.
- Report specific gravity to the nearest 0.001
- Report absorption to the nearest 0.1 percent.

ANNEX — STANDARDIZATION OF PYCNOMETER

(Mandatory Information)

- 1. Fill the pycnometer to the calibrated fill line with water at 23 ± 1.7 °C (73.4 ± 3 °F).
- 2. Dry the outside of the pycnometer.
- 3. Determine the combined mass of pycnometer and water to the nearest 0.1 g. Designate as B.